



GSE STANDARD PRODUCTS

# Product Data Sheet

## GSE HyperNet, HF, HS and UF Geonets

GSE HyperNet geonets are synthetic drainage materials manufactured from a premium grade high density polyethylene (HDPE) resin. The structure of the HyperNet geonet is formed specifically to transmit fluids uniformly under a variety of field conditions. HDPE resins are inert to chemicals encountered in most of the civil and environmental applications where these materials are used. GSE geonets are formulated to be resistant to ultraviolet light for time periods necessary to complete installation. GSE HyperNet geonets are available in standard, HF, HS, and UF varieties.

The table below provides index physical, mechanical and hydraulic characteristics of GSE geonets. Contact GSE for information regarding performance of these products under site-specific load, gradient, and boundary conditions.

### Product Specifications

TESTED PROPERTY	TEST METHOD	FREQUENCY	MINIMUM AVERAGE ROLL VALUE <sup>(b)</sup>			
			HyperNet	HyperNet HF	HyperNet HS	HyperNet UF
Product Code			XL4000N004	XL5000N004	XL7000N004	XL8000N004
Transmissivity <sup>(a)</sup> , gal/min/ft (m <sup>2</sup> /sec)	ASTM D 4716	1/540,000 ft <sup>2</sup>	9.66 (2 x 10 <sup>-3</sup> )	14.49 (3 x 10 <sup>-3</sup> )	28.98 (6 x 10 <sup>-3</sup> )	38.64 (8 x 10 <sup>-3</sup> )
Thickness, mil (mm)	ASTM D 5199	1/50,000 ft <sup>2</sup>	200 (5)	250 (6.3)	275 (7)	300 (7.6)
Density, g/cm <sup>3</sup>	ASTM D 1505	1/50,000 ft <sup>2</sup>	0.94	0.94	0.94	0.94
Tensile Strength (MD), lb/in (N/mm)	ASTM D 5035	1/50,000 ft <sup>2</sup>	45 (7.9)	55 (9.6)	65 (11.5)	75 (13.3)
Carbon Black Content, %	ASTM D 1603*/4218	1/50,000 ft <sup>2</sup>	2.0	2.0	2.0	2.0
Roll Width <sup>(c)</sup> , ft (m)			15 (4.6)	15 (4.6)	15 (4.6)	15 (4.6)
Roll Length <sup>(c)</sup> , ft (m)			300 (91)	250 (76)	220 (67)	200 (60)
Roll Area, ft <sup>2</sup> (m <sup>2</sup> )			4,500 (418)	3,750 (348)	3,300 (305)	3,000 (278)

**NOTES:**

- <sup>(a)</sup>Gradient of 0.1, normal load of 10,000 psf, water at 70° F (20° C), between steel plates for 15 minutes.
- <sup>(b)</sup>These are MARV values that are based on the cumulative results of specimens tested by GSE.
- <sup>(c)</sup>Roll widths and lengths have a tolerance of ±1%.
- \*Modified.

DS017 HyperNet R01/07/08

This information is provided for reference purposes only and is not intended as a warranty or guarantee. GSE assumes no liability in connection with the use of this information. Please check with GSE for current, standard minimum quality assurance procedures and specifications.

GSE and other trademarks in this document are registered trademarks of GSE Lining Technology, Inc. in the United States and certain foreign countries.

<b>North America</b>	GSE Lining Technology, Inc.	Houston, Texas	800.435.2008	281.443.8564	Fax: 281.230.6739
<b>South America</b>	GSE Lining Technology Chile S.A.	Santiago, Chile		56.2.595.4200	Fax: 56.2.595.4290
<b>Asia Pacific</b>	GSE Lining Technology Company Limited	Bangkok, Thailand		66.2.937.0091	Fax: 66.2.937.0097
<b>Europe &amp; Africa</b>	GSE Lining Technology GmbH	Hamburg, Germany		49.40.767420	Fax: 49.40.7674234
<b>Middle East</b>	GSE Lining Technology-Egypt	The 6th of October City, Egypt		20.2.828.8888	Fax: 20.2.828.8889