



GSE STANDARD PRODUCTS

Product Data Sheet

GSE Nonwoven Geotextiles

GSE Nonwoven Geotextiles is a family of polypropylene, staple fiber, nonwoven, needlepunched geotextiles. Manufactured using an advanced manufacturing and quality system, these products are the most uniform and consistent nonwoven, needlepunched geotextile currently available in the industry. GSE combines a fiber selection and approval system with in-line quality control and a state-of-the-art laboratory to ensure that every roll shipped meets customer specifications. The company has performed extensive performance testing to evaluate suitability of its nonwovens for various applications. GSE Nonwoven Geotextiles are available in a range of weights to meet your specific project needs. *These product specifications meet or exceed GRI GT12, GRI GT13 and AASHTO M288.*

Product Specifications

TESTED PROPERTY	TEST METHOD	FREQUENCY	NW4	NW6	NW8	NW10	NW12	NW16
Product Code			GEO 0408002	GEO 0608002	GEO 0808002	GEO 1008002	GEO 1208002	GEO 1608002
AASHTO M288 Class			3	2	1	>1	>>1	>>>1
Mass per Unit Area, oz/yd ² (g/m ²)	ASTM D 5261	90,000 ft ²	4 (135)	6 (200)	8 (270)	10 (335)	12 (405)	16 (540)
Grab Tensile Strength, lb (N)	ASTM D 4632	90,000 ft ²	120 (530)	170 (755)	220 (975)	260 (1,155)	320 (1,420)	390 (1,735)
Grab Elongation, %	ASTM D 4632	90,000 ft ²	50	50	50	50	50	50
Puncture Strength, lb (N)	ASTM D 4833	90,000 ft ²	60 (265)	90 (395)	120 (525)	165 (725)	190 (835)	240 (1,055)
Trapezoidal Tear Strength, lb (N)	ASTM D 4533	90,000 ft ²	50 (220)	70 (310)	95 (420)	100 (445)	125 (555)	150 (665)
Apparent Opening Size, Sieve No. (mm)	ASTM D 4751	540,000 ft ²	70 (0.212)	70 (0.212)	80 (0.180)	100 (0.150)	100 (0.150)	100 (0.150)
Permittivity, sec ⁻¹	ASTM D 4491	540,000 ft ²	1.50	1.50	1.50	1.20	0.80	0.70
Permeability, cm/sec	ASTM D 4491	540,000 ft ²	0.22	0.30	0.30	0.30	0.29	0.27
Water Flow Rate, gpm/ft ² (l/min/m ²)	ASTM D 4491	540,000 ft ²	120 (4,885)	110 (4,480)	110 (4,480)	85 (3,460)	60 (2,440)	50 (2,035)
UV Resistance (% retained after 500 hours)	ASTM D 4355	per formulation	70	70	70	70	70	70
Roll Length ⁽¹⁾ , ft (m)			600 (182)	600 (182)	600 (182)	300 (91)	300 (91)	300 (91)
Roll Width ⁽¹⁾ , ft (m)			15 (4.6)	15 (4.6)	15 (4.6)	15 (4.6)	15 (4.6)	15 (4.6)
Roll Area, ft ² (m ²)			9,000 (836)	9,000 (836)	9,000 (836)	4,500 (418)	4,500 (418)	4,500 (418)

NOTES:

- The property values listed are in weaker principal direction. All values listed are Minimum Average Roll Values (MARV) except apparent opening size in mm and UV resistance. Apparent opening size (mm) is a Maximum Average Roll Value. UV is a typical value.
- ⁽¹⁾Roll lengths and widths have a tolerance of ±1%.

DS037 NW R08/30/07

This information is provided for reference purposes only and is not intended as a warranty or guarantee. GSE assumes no liability in connection with the use of this information. Please check with GSE for current, standard minimum quality assurance procedures and specifications.

GSE and other trademarks in this document are registered trademarks of GSE Lining Technology, Inc. in the United States and certain foreign countries.

North America	GSE Lining Technology, Inc.	Houston, Texas	800.435.2008	281.443.8564	Fax: 281.230.6739
South America	GSE Lining Technology Chile S.A.	Santiago, Chile		56.2.595.4200	Fax: 56.2.595.4290
Asia Pacific	GSE Lining Technology Company Limited	Bangkok, Thailand		66.2.937.0091	Fax: 66.2.937.0097
Europe & Africa	GSE Lining Technology GmbH	Hamburg, Germany		49.40.767420	Fax: 49.40.7674234
Middle East	GSE Lining Technology-Egypt	The 6th of October City, Egypt		20.2.828.8888	Fax: 20.2.828.8889