



GSE STANDARD PRODUCTS

Product Data Sheet

GSE White Textured Geomembranes (Single-Sided)

GSE White Textured is the textured version of GSE White. It is a high quality, high density polyethylene (HDPE) geomembrane with one or two coextruded, textured surfaces. It has a UV-stabilized, white upper surface that is approximately 3 mils (0.125 mm) thick. This layer is part of the total thickness, the remainder of which is a carbon black stabilized primary layer. The light reflective surface improves detection of post-installation damage and reduces heat buildup on the liner by reflecting solar energy. Reducing liner temperature leads to fewer wrinkles and less subgrade desiccation. This textured product provides enhanced interface friction with adjoining materials. *These product specifications meet or exceed GRI GM13.*

Product Specifications

GSE Advantage Products

GSE GundSeal • GSE Conductive • GSE White • GSE PermaNet • GSE BioDrain System

TESTED PROPERTY	TEST METHOD	FREQUENCY	MINIMUM VALUE			
Product Code			HST 040G010	HST 060G010	HST 080G010	HST 100G010
Thickness, (minimum average) mil (mm) Lowest individual for 8 out of 10 values Lowest individual for any of the 10 values	ASTM D 5994	every roll	38 (0.96) 36 (0.91) 34 (0.86)	57 (1.45) 54 (1.40) 51 (1.30)	76 (1.93) 72 (1.80) 68 (1.73)	95 (2.41) 90 (2.30) 85 (2.16)
Density ⁽⁴⁾ , g/cm ³	ASTM D 1505	200,000 lb	0.94	0.94	0.94	0.94
Tensile Properties (each direction) ⁽¹⁾ Strength at Break, lb/in-width (N/mm) Strength at Yield, lb/in-width (N/mm) Elongation at Break, % Elongation at Yield, %	ASTM D 6693, Type IV Dumbell, 2 ipm G.L. = 2.0 in (51 mm) G.L. = 1.3 in (33 mm)	20,000 lb	60 (11) 84 (15) 100 12	90 (16) 126 (22) 100 12	120 (21) 168 (29) 100 12	150 (27) 210 (37) 100 12
Tear Resistance, lb (N)	ASTM D 1004	45,000 lb	28 (125)	42 (187)	56 (249)	70 (311)
Puncture Resistance, lb (N)	ASTM D 4833	45,000 lb	60 (267)	90 (400)	120 (534)	150 (667)
Carbon Black Content ⁽²⁾⁽⁴⁾ , %	ASTM D 1603*/4218	20,000 lb	2.0	2.0	2.0	2.0
Carbon Black Dispersion	ASTM D 5596	45,000 lb	+Note 1	+Note 1	+Note 1	+Note 1
Asperity Height	GRI GM 12	second roll	+Note 2	+Note 2	+Note 2	+Note 2
Notched Constant Tensile Load ⁽³⁾ , hr	ASTM D 5397, Appendix	200,000 lb	300	300	300	300
REFERENCE PROPERTY	TEST METHOD	FREQUENCY	NOMINAL VALUE			
Oxidative Induction Time ⁽⁴⁾ , min	ASTM D 3895, 200° C; O ₂ , 1 atm	200,000 lb	>100	>100	>100	>100
Roll Length ⁽⁵⁾ (approximate), ft (m)			650 (198)	420 (128)	320 (98)	250 (76)
Roll Width ⁽⁵⁾ , ft (m)			22.5 (6.9)	22.5 (6.9)	22.5 (6.9)	22.5 (6.9)
Roll Area, ft ² (m ²)			14,625 (1,359)	9,450 (878)	7,200 (669)	5,625 (523)

NOTES:

- +Note 1: Dispersion only applies to near spherical agglomerates. 9 or 10 views shall be Category 1 or 2. No more than 1 view from Category 3.
- +Note 2: 10 mil average. 8 of 10 readings ≥ 7 mils. Lowest individual ≥ 5 mils.
- GSE White Textured is available in rolls weighing about 3,000 lb (1,360 kg).
- ⁽¹⁾The combination of stress concentrations due to coextrusion texture geometry and the small specimen size results in large variation of test results. Therefore, these tensile properties are minimum average values.
- ⁽²⁾GSE White Textured may have an overall ash content greater than 3.0% due to the white layer.
- ⁽³⁾NCTL is conducted on representative smooth membrane samples.
- All GSE geomembranes have dimensional stability of $\pm 2\%$ when tested with ASTM D 1204 and ITB of $< 77^\circ$ C when tested with ASTM D 746.
- ⁽⁴⁾The values apply to the black layer only.
- ⁽⁵⁾Roll lengths and widths have a tolerance of $\pm 1\%$.
- *Modified.

DS015s whttextss R01/07/08

This information is provided for reference purposes only and is not intended as a warranty or guarantee. GSE assumes no liability in connection with the use of this information. Please check with GSE for current, standard minimum quality assurance procedures and specifications.

GSE and other trademarks in this document are registered trademarks of GSE Lining Technology, Inc. in the United States and certain foreign countries.

North America	GSE Lining Technology, Inc.	Houston, Texas	800.435.2008	281.443.8564	Fax: 281.230.6739
South America	GSE Lining Technology Chile S.A.	Santiago, Chile		56.2.595.4200	Fax: 56.2.595.4290
Asia Pacific	GSE Lining Technology Company Limited	Bangkok, Thailand		66.2.937.0091	Fax: 66.2.937.0097
Europe & Africa	GSE Lining Technology GmbH	Hamburg, Germany		49.40.767420	Fax: 49.40.7674234
Middle East	GSE Lining Technology-Egypt	The 6th of October City, Egypt		20.2.828.8888	Fax: 20.2.828.8889