

WPE-15 SPECIFICATION SHEET

General use for covers requiring up to 3-years exposure. Material has a LDPE coating.

Specification Listing

Product Code	WPE-15
Weight	6.1 oz/sq. yd. ASTM D-751
Finished Thickness	12 mils
Weave Count	10x10 weave
Coating Thickness	1.75 mils
Color	Black/white

Tensile Strength	Warp (Machine direction) 219 lbs. ASTM D-751 Weft (Cross direction) 200 lbs.
Elongation	Warp Weft
Tongue Tear	Warp 57 lbs. ASTM D-751 Weft 55 lbs.
Grab Tear	Warp Weft
Mullen Burst	391 lbs. ASTM D-751
UV Resistance	80% or greater after 2,000 hours

- These are typical property values and are intended as guides only. The figures listed do not represent specification limits.
- All results are +/- 10%.
- Specific batch or lot test results are available when requested in writing on the purchase order or prior to order shipment. Independent test results for any specific shipment must be arranged in advance.
- Last updated November 26, 2003.