

WPE-20 SPECIFICATION SHEET

Heavier duty cover material. Can be used as liner but under ideal conditions of sand or geotextile.

Nominal Weave	10 x 10 weave
Coating	LDPE , Two sides @ 3.0 mil thickness,
Color	Black / Silver; Black / White
Weight	8 oz/yd ² ± 5% finished weight

Product Performance:

TENSILE STRENGTH ASTM D751-grab		
	Machine Direction - Force	341 lbs
	Elongation	14%
	Cross Direction - Force	309 lbs
	Elongation	12%

TRAPEZOIDAL TEAR STRENGTH ASTM D-751 tongue		
	Machine Direction - Force	53 lbs
	Cross Direction - Force	49 lbs

UV ACCELERATED WEATHERING ASTM G154-98
 More than 90% strength retained after 2,000 hours exposure*

MULLEN BURST ASTM D-751	438 psi
NOMINAL THICKNESS	16 mils

Note: ALL VALUES ARE ± 10%

**QUV A-340 LAMPS 8 HRS UV @ 60°C, 4 Hrs condensation @ 40°C*

The test data is based on an average taken over several production runs and should not be considered or interpreted as minimum or maximum values. Values are typical data and not limiting specifications. Independent lab test results for a specific shipment can be arranged in advance.